

PRODUCT SPECIFICATION

CAST-IN-PLACE PAVER



Detectable Warning Systems

Wet Set (Cast-In-Place) Specifications:

SIZE WxLxD	PART NUMBER	STANDARD COLORS	CUSTOMIZABLE
24"x36"x1/4"	EQL-24x36	FEDERAL YELLOW, BRICK RED, BLUE, DK GREY, LT GREY, BLACK	YES
24"x48"x1/4"	EQL-24x48	FEDERAL YELLOW, BRICK RED, BLUE, DK GREY, LT GREY, BLACK	YES
24"x60"x1/4"	EQL-24X60	FEDERAL YELLOW, BRICK RED, BLUE, DK GREY, LT GREY, BLACK	YES
36"x48"x1/4"	EQL-36X48	FEDERAL YELLOW, BRICK RED, BLUE, DK GREY, LT GREY, BLACK	YES
36"x60"x1/4"	EQL-36x60	FEDERAL YELLOW, BRICK RED, BLUE, DK GREY, LT GREY, BLACK	YES

Product Features

- ☑ 5 Year Manufacturer Warranty
- ☑ Durable & Strong
- ☑ Ease Of Install
- ☑ Simple Replacement & Re-Coating
- ☑ Ships Nationwide
- ☑ Sent Complete With Color Matching Anchors And/Or Adhesive
- ☑ Manufactured With Over 100 Years Of Combined Experience In Production, Sales, Installation And Maintenance
- ☑ Guaranteed Satisfaction

Wet Set (Cast-In-Place) Technical Data:

TEST DESCRIPTION	TEST METHOD	VALUE (Nominal)
COMPRESSION STRENGTH	ASTM D 695	21,100 PSI
WATER ABSORPTION	FM 5-D570	0.1%
FLEXURAL STRENGTH	ASTM D 790	20,000 PSI
FLEXURAL MODULUS	ASTM D 790	5.0 x 10 ⁵
TENSILE STRENGTH	ASTM D 638	10,000 PSI
TENSILE MODULUS	ASTM D 638	5.0 x 10 ⁵
TENSILE ELONGATION	ASTM D 638	3.0%
HDT	ASTM D 648	170 DEGREES FAHRENHEIT
HARDNESS, BARCOL 934-1	ASTM D 2583	35
SLIP RESISTANCE	FM 3-C1028	1.03 DRY, 0.73 WET
WEAR RESISTANCE	FM 5-594	0.031 cm ³
SALT SPRAY	ASTM B 117	NO CHANGE (200 HOURS)
LOAD BEARING @ 16K LBS	AASHTO-H20	NO DAMAGE
CHEMICAL STAIN TESTING	ASTM D 543	NO DETERIORATION
ABRASION RESISTANCE	ASTM C 501	435
EPA (RCRA)	EPA-1311, EPA-6010D, EPA-7470A	MEETS REGULATIONS